

CORRECTED VERSION

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
15 September 2005 (15.09.2005)

PCT

(10) International Publication Number
WO 2005/085347 A1

(51) International Patent Classification⁷: **C08L 67/00**,
23/00, 23/08, 67/02, 67/03, 67/04

(21) International Application Number:
PCT/JP2005/004168

(22) International Filing Date: 3 March 2005 (03.03.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
2004-068009 10 March 2004 (10.03.2004) JP

(71) Applicants (*for all designated States except US*): **MATSUSHITA ELECTRIC WORKS, LTD.** [JP/JP]; 1048, Oaza-Kadoma, Kadoma-shi, Osaka, 5718686 (JP). **SUMITOMO CHEMICAL COMPANY, LIMITED** [JP/JP]; 27-1, Shinkawa 2-chome, Chuo-ku, Tokyo, 1048260 (JP).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **IKEGAWA, Naoto** [JP/JP]; c/o Matsushita Electric Works, Ltd., 1048, Oaza-Kadoma, Kadoma-shi, Osaka 5718686 (JP). **OKAMOTO, Satoshi** [JP/JP]; c/o Sumitomo Chemical Company, Limited, 6, Kitahara, Tsukuba-shi, Ibaraki 3003294 (JP). **KATAGIRI, Shiro** [JP/JP]; c/o Sumitomo Chemical Company, Limited, 6, Kitahara, Tsukuba-shi, Ibaraki 3003294 (JP).

(74) Agents: **NISHIKAWA, Yoshiakiyo** et al.; Hokuto Patent Attorneys Office Umeda-Daiichiseimei Bldg. 5th Floor, 12-17, Umeda 1-chome, Kita-ku, Osaka-shi, Osaka 5300001 (JP).

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

(48) Date of publication of this corrected version:

24 November 2005

(15) Information about Correction:

see PCT Gazette No. 47/2005 of 24 November 2005, Section II

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: RESIN MOLDED ARTICLE WITH REDUCED DIELECTRIC LOSS TANGENT AND PRODUCTION METHOD THEREFOR

(57) Abstract: A resin molded article having a reduced dielectric loss tangent is provided. This resin molded article is obtained by performing a heat treatment to a resin composition comprising a liquid-crystalline polyester and an epoxy-group containing ethylene copolymer at a temperature lower than a flow-beginning temperature of the liquid-crystalline polyester, preferably at a temperature between a lower limit temperature calculated by subtracting 120°C from the flow-beginning temperature and an upper limit temperature calculated by subtracting 20°C from the flow-beginning temperature. This resin molded article has a smaller dielectric loss tangent than the resin molded article obtained from the resin composition without the heat treatment.



WO 2005/085347 A1